

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 September 2003 (18.09.2003)

PCT

(10) International Publication Number
WO 03/076508 A1

(51) International Patent Classification⁷: **C08L 23/10**,
23/04, 23/16, C08J 5/18

(21) International Application Number: PCT/EP03/02299

(22) International Filing Date: 5 March 2003 (05.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02075991.6 12 March 2002 (12.03.2002) EP

(71) Applicant (for all designated States except US): **BASELL
POLIOLEFINE ITALIA S.P.A.** [IT/IT]; Via Pergolesi,
25, I-20124 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **PELLICONI, An-
teo** [IT/IT]; Via Volta, 22, I-45030 Occhiobello (IT). **AN-
GELINI, Antonella** [IT/IT]; Via Val Trebbia, 16, I-44100
Ferrara (IT).

(74) Agent: **COLUCCI, Giuseppe**; Basell Poliolefine Italia
S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100
Ferrara (IT).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN,
YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: POLYOLEFIN COMPOSITIONS HAVING HIGH FLUIDITY

(57) Abstract: A polyolefin composition suitable for preparing films and sheets, comprising: (A) from 15 to 40 % by weight of a crystalline copolymer of propylene with at least one alpha-olefin of formula $H_2C=CHR^1$, where R^1 is H or a C_{2-8} linear or branched alkyl, containing at least 90 % by weight of propylene, having solubility in xylene at room temperature lower than 15% by weight; (B) from 60 to 85 % by weight of an elastomeric fraction comprising: (1) a copolymer of propylene with ethylene, optionally containing 0.5 to 5 % by weight of a diene, containing from 20 to 35 % by weight ethylene, and having solubility in xylene at room temperature greater than 45% by weight, the intrinsic viscosity of the xylene soluble fraction ranging from 1.0 to 3.9 dl/g; and (2) a copolymer of ethylene with at least one alpha-olefin of formula $H_2C=CHR^2$, where R^2 is a C_{2-8} linear or branched alkyl, optionally containing 0.5 to 5 % by weight of a diene, containing 15 % to 40 % by weight alpha-olefin, and having solubility in xylene at room temperature greater than 35% by weight, the intrinsic viscosity of the xylene soluble fraction ranging from 1.0 to 3.0 dl/g; the (1)/(2) weight ratio ranging from 1:5 to 5:1. The polyolefin composition of the invention, preferably prepared by sequential polymerization in at least three stages, has a flexural modulus lower than 130 Mpa, shore D hardness lower than 40, and MFR ≥ 1.5 g/10min.